

# Facemount®

Facemount® is a 1 mil (25µ) high quality, optically clear PET film, coated on both sides with a pressure sensitive, permanent solvent acrylic adhesive, both of which are protected by a clear PET release liner. Facemount® is made using the finest optical clarity components. It offers excellent UV stability to graphic prints.

- RECOMMENDED FOR SECOND SURFACE MOUNTING (COMMONLY REFERRED TO AS FACE MOUNTING) OF IMAGES TO CLEAR SUBSTRATES, SUCH AS PETG™, PLEXIGLAS™, ACRYLIC, POLYCARBONATE, AND GLASS.
- IDEAL FOR LENTICULAR IMAGING APPLICATIONS, BACKLIT DISPLAY TRANSPARENCIES, TOUCH SCREEN DISPLAYS, AND HIGH QUALITY PHOTOGRAPHIC AND INKJET PRINTED IMAGES
- SUITABLE FOR INDOOR AND SHORT-TERM OUTDOOR USE

For more information, performance and warranty guide lines please contact your local Drytac office.

© 2018 Drytac Corporation. E&OE.  
All other trademarks are the property of their respective owners.

## TECHNICAL SPECIFICATION

### PRODUCT STRUCTURE

Release Liner	Siliconized 1 Side PET
Adhesive	Permanent Solvent Acrylic (Pressure Sensitive)
Film	Clear PET
Adhesive	Permanent Solvent Acrylic (Pressure Sensitive)
Release Liner	Siliconized 1 Side PET

### PRODUCT CHARACTERISTIC

Film Thickness	1 mil (25µ)	2.8 mil (71µ)
Adhesive Layer	0.9 mil (23µ)	
Film/Adhesive Ratio	0.9:1:0.9	
UV Protection Factor	UV Stable	
Outdoor Durability	2 years	
Peel Strength (20 min, FTM1)	12.8 N/25mm (glass 24 hours)	
Service Temperature Range	-40°F to 212°F (-40°C to 100°C)	
Shelf Life	1 year	
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity	

### PROCESS SETTING

#### Roller Laminator

Temperature: Room Temperature to 104°F (40°C)  
Speed: 1 ft to 8 ft (0.3m to 2.5m) per minute

#### Press

Not Recommended

# DRYTAC®

## ADHESIVE SCIENCE

#### Europe

Filwood Road,  
Fishponds,  
Bristol, BS16 3RY,  
United Kingdom  
[bristol@drytac.com](mailto:bristol@drytac.com)  
Tel: +44 (0) 117 958 6500

#### Canada

105 Nuggett Court,  
Brampton,  
Ontario, L6T 5A9,  
Canada  
[toronto@drytac.com](mailto:toronto@drytac.com)  
Tel: +1 800.353.2883

#### USA

5601 Eastport Boulevard,  
Richmond,  
Virginia, 23231,  
USA  
[customerservice@drytac.com](mailto:customerservice@drytac.com)  
Tel: +1 800.280.6013

[www.drytac.com](http://www.drytac.com)